

FORM 270-90
REV. 10-91

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY'S Docket NUMBER

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

AD-6506

U.S. APPLICATION NO (If known, see 37 CFR 1.5)

09/180943

INTERNATIONAL APPLICATION NO

PCT/US97/09090

INTERNATIONAL FILING DATE

16 MAY 1997 (16.05.97)

PRIORITY DATE CLAIMED

24 MAY 1996 (24.05.96)

TITLE OF INVENTION AROMATIC POLYAMIDE RESIN COMPOSITION HAVING EXCELLENT BALANCE OF
TOUGHNESS AND STIFFNESS

APPLICANT(S) FOR DO/EO/US

NOZAKI, Masahiro

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4. ☒ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☒ A copy of the International Application as filed (35 U.S.C. 371(c)(2))
 - a. ☐ is transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ has been transmitted by the International Bureau.
 - c. ☒ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☐ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ have been transmitted by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☒ have not been made and will not be made.
8. ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10. ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11. to 16. below concern document(s) or information included:

11. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12. ☒ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included
13. ☐ A **FIRST** preliminary amendment.
☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
14. ☐ A substitute specification.
15. ☐ A change of power of attorney and/or address letter.
16. ☒ Other items or information:
 - A. INTERNATIONAL PRELIMINARY EXAMINATION REPORT
 - B. INTERNATIONAL PUBLISHED APPLICATION W097/44395
 - C. GENERAL POWER OF ATTORNEY

NOVEMBER 18, 1998

U.S. APPLICATION NO. (if known see 37 CFR 1.51)		INTERNATIONAL APPLICATION NO. PCT/US97/09090		ATTORNEY'S DOCKET NUMBER AD6506	
17. <input type="checkbox"/> The following fees are submitted: BASIC NATIONAL FEE (37 CFR 1.492(a)(1)-(5)): Search Report has been prepared by the EPO or JPO \$930.00 International preliminary examination fee paid to USPTO (37 CFR 1.482) \$720.00 No international preliminary examination fee paid to USPTO (37 CFR 1.482) but international search fee paid to USPTO (37 CFR 1.445(a)(2)) \$790.00 Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$1070.00 International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(2)-(4) \$98.00 ENTER APPROPRIATE BASIC FEE AMOUNT =				CALCULATIONS PTO USE ONLY	
Surcharge of \$130.00 for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(e)).				\$	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total claims	4 - 20 =		X \$22.00	\$	
Independent claims	1 - 3 =		X \$82.00	\$	
MULTIPLE DEPENDENT CLAIM(S) (if applicable)				\$270.00	\$ 270.00
TOTAL OF ABOVE CALCULATIONS =				\$	1200.00
Reduction of 1/2 for filing by small entity, if applicable. Verified Small Entity Statement must also be filed (Note 37 CFR 1.9, 1.27, 1.28).				\$	
SUBTOTAL =				\$	1,200.00
Processing fee of \$130.00 for furnishing the English translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(f)).				\$	
TOTAL NATIONAL FEE =				\$	1,200.00
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property				+	\$
TOTAL FEES ENCLOSED =				\$	1,200.00
				Amount to be:	\$
				refunded	
				charged	\$

- a. ☐ A check in the amount of \$ _____ to cover the above fees is enclosed.
- b. ☒ Please charge my Deposit Account No. 04-1928 in the amount of \$ 1,200.00 to cover the above fees. A duplicate copy of this sheet is enclosed.
- c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 04-1928. A duplicate copy of this sheet is enclosed.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status. REG. NO. 31,825

SEND ALL CORRESPONDENCE TO

E.I.DUPONT DE NEMOURS AND COMPANY
 LEGAL PATENT RECORD CENTER
 1007 MARKET STREET
 WILMINGTON, DELAWARE 19898



SIGNATURE CRAIG H. EVANS

FOR: JAMES A. FORSTNER

NAME

24,259

REGISTRATION NUMBER

TITLEAROMATIC POLYAMIDE RESIN COMPOSITION HAVING
EXCELLENT BALANCE OF TOUGHNESS AND STIFFNESS

5

BACKGROUND OF THE INVENTION

The present invention relates to aromatic polyamide resin compositions which are widely used in covers, gears, structural materials, automotive parts requiring hydrolysis resistance and other automotive parts, covers, gears and other electronic parts, sinks and other furniture parts for industrial or domestic use, and
10 table tops, desk tops, kitchen tops and other plate-shaped applications that require dimensional accuracy, heat resistance, chemical resistance, toughness and stiffness.

The technology to improve the stiffness of molded products by blending glass fibers, talc and other inorganic fillers in a polyamide resin has been widely
15 known.

Furthermore, for the molded articles obtained by molding a polyamide resin composition blended with glass fibers, especially large molded articles, warping occurs because of shrinkage anisotropy. In order to solve the problem of warping, an inorganic filler with a small aspect ratio has been used. However, in
20 this case, a problem occurs in which the impact resistance of the molded articles is markedly decreased.

On the other hand, many technologies related to the improvement of the impact resistance by the addition of a variety of additives into an aliphatic polyamide resin have been known. Specifically, there is a polyamide resin
25 composition (Japanese Kokoku Patent No. Sho 42[1967]-12546) consisting of a blend of 50-99 wt% of a polyamide resin and 50-1 wt% of an olefin copolymer which contains 0.1-10 mol% of acid groups. Furthermore, there is a polyamide resin composition (Japanese Kokoku Patent No. Sho 55[1980]-44108) consisting of 60-99 wt% of an aliphatic polyamide resin and 1-40 wt% of a mixture,
30 containing at least one polymer which is a certain type branched-chain or straight-chain polymer with a tensile modulus in the range of about 1.0-20,000 psi, having particle size in the range of 0.01-1.0 micron, and having positions adhered to the polyamide resin, with the ratio of the tensile modulus of the polyamide matrix resin to the tensile modulus of at least one of the polymers
35 being larger than 10:1, at least one of the polymers in the blend being 20 wt%, and the remainder being other blendable polymers as a diluent.

Moreover, the blending properly of an inorganic filler and an impact modifier into an aliphatic polyamide resin is also a commonly used technology among skilled persons in the field.

However, attempts to blend an inorganic filler and an impact modifier into an aromatic polyamide resin have not been conducted conventionally. Attempts to provide a resin composition with an excellent balance in stiffness and toughness by blending these additives, without causing deterioration of the excellent heat resistance and chemical resistance of the aromatic polyamide, has not been as easy as blending these additives into the aliphatic polyamides.

Here, the present invention has an objective of providing an aromatic polyamide resin composition with an excellent balance in toughness and stiffness, without the warping problem of molded products, while maintaining the excellent heat resistance and chemical resistance of the aromatic polyamide resin, especially by specifying the blending ratio of the inorganic filler and the impact modifier, in order to solve the above-mentioned problems.

SUMMARY OF THE INVENTION

This invention provides aromatic polyamide resin compositions comprising an aromatic polyamide resin having a melting point of at least 290°C; an inorganic filler; and an impact modifier or impact modifying additive.

Preferred are such compositions wherein the ratio of the weight (M) of said inorganic filler to the weight (T) of said impact modifier is $2.0 \leq M/T \leq 6.5$.

It is further preferred that the melt viscosity of the composition, measured with a capillary rheometer at a shear rate of 1000/second and at a process temperature 20-30°C. higher than the melting point of the aromatic polyamide resin, is 350 Pa·sec or less. It is still further preferred that the resin in said composition has a glass transition temperature of at least 60°C.

DETAILED DESCRIPTION

As used herein the term "polyamide resin composition" means polyamide resins mixed with other materials. "Polyamide resin" means the polymer alone. "Impact modifier" means a material which, when incorporated with resin into the composition, improves impact performance of compositions lacking the impact modifier.

In order to solve the above-mentioned problems, the polyamide resin composition of the present invention is obtained by blending an aromatic polyamide resin having a melting point of at least 290°C, an inorganic filler, and an impact modifier.

As the monomers constituting the aromatic polyamide resins used in the aromatic polyamide resin compositions of the present invention, aromatic diamines, such as p-phenylenediamine, o-phenylenediamine, m-phenylenediamine, p-xylenediamine, m-xylenediamine, etc., aromatic dicarboxylic acids, such as terephthalic acid, isophthalic acid, phthalic acid, 2-methylterephthalic acid, naphthalenedicarboxylic acid, etc., and aromatic aminocarboxylic acids such as p-aminobenzoic acid, etc., can be mentioned. These aromatic monomers can be used alone or in combination of two or more.

Furthermore, as long as the melting point of the obtained aromatic polyamide is at least 290°C, monomers other than aromatic monomers may be used in combination in the above-mentioned aromatic monomers. As the monomers other than the above-mentioned aromatic monomers, aliphatic dicarboxylic acids, aliphatic alkylenediamines, alicyclic alkylenediamines, and aliphatic aminocarboxylic acids can be contained. As the aliphatic dicarboxylic acids, adipic acid, sebacic acid, azelaic acid, dodecane diacid, etc. can be used. These can be used alone or in combination of two or more. Furthermore, the aliphatic alkylenediamine and dicarboxylic acid components may be in a straight-chain shape or a branched-chain shape. These may be used alone or in combination of two or more. Specific examples of these aliphatic alkylenediamines, are ethylenediamine, trimethylenediamine, tetramethylenediamine, pentamethylenediamine, hexamethylenediamine, 1,7-diaminoheptane, 1,8-diaminooctane, 1,9-diaminononane, 1,10-diaminodecane, 2-methylpentamethylenediamine, 2-ethyltetramethylenediamine, etc. Specific examples of the alicyclic alkylenediamine components are 1,3-diaminocyclohexane, 1,4-diaminocyclohexane, 1,3-bis(aminomethyl) cyclohexane, bis(aminomethyl)cyclohexane, bis(4-aminocyclohexyl) methane, 4,4'-diamino-3,3'-dimethyldicyclohexylmethane, isophoronediamine, piperazine, etc. These can be used alone or in combination of two or more. Specific examples of aminocarboxylic acid components are ϵ -aminocaproic acid, omega-aminoundecanoic acid, etc.

The preferred aromatic polyamide resins that can be used in the aromatic polyamide resin compositions of the present invention are, a polyamide with terephthalic acid preferably used as an aromatic dicarboxylic acid, a polyamide resin consisting of terephthalic acid, hexamethylenediamine and 2-methylpentamethylenediamine, a polyamide resin consisting of terephthalic acid, adipic acid, and hexamethylenediamine, a polyamide resin consisting of terephthalic acid, isophthalic acid and hexamethylenediamine, and a polyamide

resin consisting of terephthalic acid, isophthalic acid, adipic acid and hexamethylenediamine. The contents of the various monomer components can be appropriately decided so that the melting point of the aromatic polyamide resin is at least 290°C. For an aromatic polyamide with a melting point lower than

5 290°C, there is a problem in heat resistance. Furthermore, an aromatic polyamide with a glass transition temperature of at least 60°C is preferred so that the chemical resistance will not deteriorate. In the manufacture of an aromatic polyamide with a high glass transition temperature, it is necessary to increase the content of the aromatic monomer components in the aromatic polyamide resin.

10 For example, an aromatic polyamide resin consisting of terephthalic acid as the carboxylic acid component, and 2-methylpentamethylenediamine and hexamethylenediamine as a diamine component and terephthalic acid has a higher glass transition temperature than an aromatic polyamide resin consisting of terephthalic acid and adipic acid as the carboxylic acid components and
15 hexamethylenediamine as the diamine component. Thus, in applications in which chemical resistance is especially desired, an aromatic polyamide resin consisting of terephthalic acid as the carboxylic acid component and 2-methylpentamethylenediamine and hexamethylenediamine as the diamine component can be used preferably.

20 Moreover, the aromatic polyamide resin of the present invention includes a blend obtained by bending two or more aromatic polyamide resins obtained from the various above-mentioned monomer components, and a blend of an aromatic polyamide resin and an aliphatic polyamide resin. However, the melting point of the blend must be at least 290°C.

25 The inorganic fillers of the present invention are those customarily used in the reinforcement of engineering plastics. Specifically, glass fibers, glass flakes, kaolin, clay, talc, wollastonite, calcium carbonate, silica, carbon fibers, potassium titanate, etc. are available. Kaolin and clay are preferred.

As impact modifiers, in general, elastomers can be used. For example, an
30 elastomer consisting of ethylene- α -olefin, an elastomer consisting of ethylene-propylene-diene, an elastomer consisting of ethylene-unsaturated carboxylic acid, an elastomer consisting of ethylene-unsaturated carboxylic acid ester, an elastomer consisting of ethylene-unsaturated carboxylic acid-unsaturated carboxylic acid ester, an elastomer consisting of α -olefin-unsaturated carboxylic
35 acid, an elastomer consisting of α -olefin-unsaturated carboxylic acid ester, an elastomer consisting of α -olefin-unsaturated carboxylic acid-unsaturated carboxylic acid ester, an elastomer consisting of ethylene- α -olefin-unsaturated carboxylic acid-unsaturated carboxylic acid ester; and graft modified materials of

- the above-mentioned elastomers. Two or more of unmodified elastomers or modified elastomers may also be blended. At least one of the above-mentioned unmodified elastomers and at least one of the above-mentioned modified elastomers may also be blended. Preferably, an elastomer consisting essentially of ethylene-propylene-diene modified with carboxylic acid-carboxylic acid anhydride can be used. The elastomer consisting essentially of ethylene-propylene-dienes modified with carboxylic acid-carboxylic acid anhydride, may be, for example, a mixture of ethylene/propylene/1,4-hexadiene-g-maleic anhydride/ethylene/propylene/1,4-hexadiene and ethylene/maleic anhydride; a mixture of ethylene/propylene/1,4-hexadiene and ethylene/propylene/1,4-hexadiene-g-maleic anhydride; ethylene/propylene/1,4-hexadiene/norbornadiene-g-maleic anhydride fumaric acid; ethylene/1,4-hexadiene/norbornadiene-g-maleic anhydride monoethyl ester; ethylene/propylene/1,4-hexadiene/norbornadiene-g-fumaric acid; a mixture of ethylene/propylene/1,4-hexadiene and ethylene/monoethylester of maleic anhydride; a mixture of ethylene/propylene/1,4-hexadiene and ethylene/maleic acid monobutyl ester; a mixture of ethylene/propylene/1,4-hexadiene and ethylene/maleic anhydride, etc.
- Furthermore, polyethylene, polypropylene and other polyolefins and their copolymers or ionomers of polyolefin copolymers, and styrene-type elastomers can also be appropriately used as impact modifiers. The preferred ionomers of polyolefin copolymers are the ionomers consisting of an ethylene unit, a derivative unit of an α,β -ethylenic unsaturated carboxylic acid, and an ester unit.
- Even more preferably, the derivative units of the α,β -ethylenic unsaturated carboxylic acids are one or more derivatives of α,β -ethylenic unsaturated carboxylic acids selected from a group consisting of a monocarboxylic acid having a carboxylic acid group ionized by the neutralization of metal ions and a dicarboxylic acid having carboxylic acid groups ionized by the neutralization of metal ions and having ester groups, as α,β -ethylenic unsaturated carboxylic acids with 3-8 carbon atoms. As the ester units, ionomers as C_{4-22} acrylic esters or methacrylic esters can be used. As the styrene-type elastomers, block copolymers constituted by monomers such as styrene-isobutylene/styrene-hydrogenated polyolefin, etc. can be used. The above-mentioned impact modifiers can be used alone or as mixtures of two or more.

It is preferable to blend the above-mentioned inorganic fillers and the above-mentioned impact modifiers so that the ratio of the weight M of the inorganic filler to the weight T of the impact modifier is $2.0 \leq M/T \leq 6.5$, even

- more preferably $2.5 \leq M/T \leq 6.0$. If M/T is less than 2.0, it will be too soft and a ejectability defect of the molded article will occur. If ejection is conducted unreasonably, deformation will occur. Moreover, heat resistance will deteriorate. If it exceeds 6.5, impact resistance will be insufficient and molding will be
- 5 difficult as well. By deciding the blending amounts of the inorganic fillers and the impact modifier within the range of M/T specified in the present invention, no warping problem will occur. An aromatic polyamide resin composition with an excellent balance in toughness and stiffness without damaging the original excellent heat resistance of the aromatic polyamide resin can be provided.
- 10 If the composition of the present invention is used to mold kitchen sinks or other large-scale molded articles, it is preferable to adjust the aromatic melt viscosity to 350 Pa·sec or less, measured with a capillary rheometer at a shear rate of 1000/sec and the process temperature. In the case of large-scale molded
- 15 molding is long, short shot and other problems will occur if the melt viscosity is not adjusted to 350 Pa·sec or less. Here, the process temperature is 20-30°C higher than the melting point of the aromatic polyamide resin used.
- In order to inhibit the color change of the molded articles formed from the composition of the present invention and to improve heat resistance and aging
- 20 characteristics, it is acceptable to further blend 0.01-2.0 wt% of metal salts of phosphoric acid, phosphorous acid or hypophosphorous acid in the above-mentioned components.
- Furthermore, to an extent not deteriorating the characteristics of the aromatic polyamide composition of the present invention, in addition to the
- 25 above-mentioned components, a thermal stabilizer, a plasticizer, an antioxidant, a nucleating agent, a dye, a pigment, a mold-releasing agent, and other additives may be blended.
- The aromatic polyamide resin composition of the present invention can be manufactured by any well-known manufacturing methods. For examples, by
- 30 using a twin-screw extruder, an aromatic polyamide resin, a filler, and an impact modifier may be simultaneously blended. An aromatic polyamide resin and a filler, and an aromatic polyamide resin and an impact modifier may be separately blended, and the blends are melted and extruded together with a twin-screw or single-screw extruder. Moreover, a pellet made from an aromatic polyamide resin
- 35 and a filler manufactured by a twin-screw extruder and a pellet made from an aromatic polyamide resin and an impact modifier may also be mixed and supplied to a molding machine for the manufacture of a molded article. Furthermore, in a molding machine with the installation of an appropriate screw, an aromatic

polyamide resin, a filler and an impact modifier are supplied directly for the manufacture of a molded article.

EXAMPLES

- 5 The present invention will be explained by the following examples.
However, the present invention is not restricted these examples.

Examples 1-8 and Comparative Examples 1-5

- 10 The various components shown in Table I were melted and kneaded in a twin-screw extruder (TEX-44, manufactured by Nippon Steel Co.). After water cooling, pellets were manufactured. The melt viscosities of the obtained pellets were measured with a capillary rheometer at a shear rate of 1000/sec and 330°C. Also the obtained pellets were molded into 13 mm x 130 mm x 3.2 mm test specimens at a mold temperature of 140°C. After holding the molded test
15 specimens at 23°C and a relative humidity of 50% for 48 h, the shrinkage ratio F in the direction of the resin flow during molding and the shrinkage ratio V in the perpendicular direction with respect to the resin flow direction were measured. If the value of F/V is near 1, no warping will occur in the molded articles. Moreover, using the obtained test specimens, the following physical properties
20 were measured according to the test methods in the following. The test results of the obtained examples are shown in Table I. The test results of comparative examples are shown in Table II.

- Heat deflection temperature, JIS K7207 (4.6 kg/cm² load)
25 Flexural Modulus ASTM D 790
Unnotched Izod impact strength ASTM D 256
Tensile strength ASTM D 638
Elongation ASTM D 638

- 30 By using the above-mentioned pellets, 75 mm x 125 mm x 3.2 mm test specimens were molded at a mold temperature of 160°C. After holding the molded test specimens at 23°C and a relative humidity of 50% for 48 h, up to 40 mm of the long-side direction of the test specimens were fixed with a jack. A steel ball with a diameter of 10 cm and a weight of 1 kg was allowed to fall. The
35 height of the ball at which the test specimens ruptured was measured. This was the falling-ball impact strength. The measured results for the examples are shown in Table I. Measured results for the comparative examples are shown in Table II.

The various components of Table I and Table II are as follows:

Polymer A:

- 5 An aromatic polyamide (manufactured by Du Pont Co., melting point 305°C, and glass transition temperature 125°C) consisting of terephthalic acid/hexamethylenediamine and terephthalic acid/2-methylpentamethylenediamine (terephthalate acid/hexamethylene diamine: terephthalic acid/2-methylpentamethylenediamine is 50:50)

10 Polymer B:

- An aromatic polyamide (manufactured by Mitsui Petrochemical Ind. Co, Ltd., Arlene® C 2000, melting point 310°C, glass transition temperature 80°C) consisting of terephthalic acid/hexamethylenediamine and adipic acid/hexamethylenediamine (terephthalic acid/hexamethylenediamine:adipic acid/hexamethylenediamine is 55:45)

Inorganic Filler:

- 20 Clay (manufactured by Engelhard Co., Translink 555)
Grass fibers (manufactured by Nippon Plate Glass Co., Ltd., 3-mm long chopped strands)

Impact Modifiers:

- 25 Ionomer (manufactured by Du Pont Co., Surlyn® 9320).
EPDM rubber (Ethylene/propylene/diene monomer copolymer, TRX-101, manufactured by Du Pont Co.)
Olefin rubber (a polyolefin type impact modifier manufactured by Mitsui Petrochemical Co., Ltd., Tafmer® 0620)

Table I

	Example 1	Example 2	Example 3	Example 4	Example 5	Example 6	Example 7	Example 8
	Polymer A	Polymer A	Polymer A	Polymer A	Polymer B	Polymer A	Polymer A	Polymer A
Aromatic polyamide	25	25	25	30	25	25	25	25
Clay (wt%)	10	7.5	5	5	0	0	0	0
Ionomers (wt%)	0	0	0	0	7.5	7.5	6	0
EPDM rubber (wt%)	0	0	0	0	0	0	0	7.5
Olefin rubber (wt%)	2.5	3.3	5	6	3.3	3.3	4.2	3.3
M/T	230	280	248	260	325	320	290	320
Melt viscosity Pa-sec								
Molding Shrinkage								
Flow direction shrinkage ratio F(%)	1.04	1.04	1.05	0.86	1.48	1.05	-	0.98
Perpendicular direction shrinkage ratio V(%)	0.88	0.95	0.92	0.75	1.41	0.95	-	0.84
F/V	1.2	1.1	1.1	1.2	1.1	1.1	-	1.2
Heat deflection temperature (°C)	235	238	247	249	240	239	241	238
Flexural modulus (kg/cm ²)	32,900	33,550	46,900	49,900	36,400	35,330	36,700	33,410
Falling-ball impact strength(cm)	>100	>100	80	70	>100	>100	>100	>100
Unnotched Izod impact strength (kg cm/cm)	191.6	187.6	112.5	100.6	138.5	184.6	185.5	177.0
Tensile strength (kg/cm ²)	870	880	1060	970	800	850	900	850
Elongation (%)	9.8	7.4	5.2	2.9	4.6	6.0	5.6	5.5

Table II

	Comparative Example 1	Comparative Example 2	Comparative Example 3	Comparative Example 4	Comparative Example 5
	Polymer A	Polymer A	Polymer A	Polymer A	Polymer A
Aromatic polyamide	25	0	0	25	25
Clay (wt%)		35			
Glass fibers (wt%)	0		0	20	3.5
Ionomers (wt%)	0	0	20	0	0
EPDM rubber (wt%)	0	0	0	0	0
Olefin rubber (wt%)	0	0	0	1.3	7.1
M/T	220	-	-	-	-
Melt viscosity (Pa·sec)					
Molding Shrinkage					
Flow direction shrinkage ratio F (%)	1.00	0.22			-
Perpendicular direction shrinkage ratio V (%)	0.88	0.74	Molding Impossible	Molding Impossible	-
F/V	1.2	0.3	"	"	-
Heat deflection temperature (°C)	254	0	"	"	-
Flexural modulus (kg/cm ²)	50,000	117,000	"	"	51,000
Falling-ball impact strength (cm)	<60	<60	"	"	<60
Unnotched Izod impact strength (kg·cm/cm)	82.0	104.8	"	"	80.0
Tensile strength (kg/cm ²)	1010	2400	"	"	1010
Elongation (%)	2.8	2.5	"	"	2.80

It is seen from Examples 1-8 that the composition of the examples have an excellent balance in stiffness as shown by the values of the deflection temperature under load and the flexural modulus, and in toughness shown by the values of the falling-ball impact strength and the unnotched Izod impact strength. The value of F/V showing the molding shrinkage was 1.1 or 1.2. It was found that no warping occurred in the molded articles. Furthermore, it was found that the mechanical characteristics shown by the tensile strength and the elongation did not deteriorate either. Moreover, Examples 1-8 and Comparative Examples 1 and 2 were compared. If only an inorganic filler was contained, the deflection temperature under load and the flexural modulus increased so that a molded article with excellent stiffness could be provided. In Comparative Examples 1 and 2, the falling-ball impact strength was as low as under 60 cm, the value of the unnotched Izod impact strength was also low. It was found that toughness deteriorated. Furthermore, if only an impact modifier was contained as in Comparative Example 3, it was found that molding was impossible. In Comparative Example 4, if the value of M/T was less than 2, the protrusion of the resin was difficult and moldability was poor. Comparative Example 5 shows that if the value of M/T exceeded 6, the values of the falling-ball impact strength and the unnotched Izod impact strength were low, and the toughness was insufficient.

Examples 9-10, and Comparative Examples 6-7

The above-mentioned polymer A, EPDM rubber 7.5 wt%, clay 25 wt%, and sodium hypophosphite 0.2 wt% were melted and kneaded with a biaxial extruder (TEX-44, manufactured by Nippon Steel Mfg. Co.). After water cooling, pellets were manufactured. By using the obtained pellets, 13 mm x 130 mm x 3.2 mm test specimens were molded at a mold temperature of 140°C. After holding the molded test specimens at 23°C and a relative humidity of 50% for 48 h, the unnotched Izod impact strength was measured. This was regarded as the initial value. Next, the test specimens were placed in an oven at 90°C or 110°C. After the time shown in Table III had elapsed, the unnotched Izod impact strength was measured. The results are shown in Table III.

Table III

	Example 9	Comparative Example 6	Example 10	Comparative Example 7
Temp. (°C)	90	90	110	110
Unnotched Izod Impact Strength (kg cm/cm)				
During Molding	187.3	184.6	187.3	184.6
After 1 week	207.3	129.2	204.0	9.0
After 2 weeks	245.2	32.8	211.8	9.1
After 4 weeks	230.0	13.1	148.7	9.5
After 8 weeks	177.4	7.1	-	-

The results shown in Table III show that, by blending sodium hypophosphite, heat resistance and aging characteristics were remarkably improved.

Example 11, Comparative Example 8

The test specimens prepared in the same manner as in Example 9 were placed in an oven at 90°C. After the time shown in Table IV had elapsed, the color difference was measured. The color difference, by using the color difference formula (JIS Z 8730) of the Lab table color system, was calculated as the difference (ΔE) of the measured value during molding. The results are shown in Table IV.

Table IV

	Example 11	Comparative Example 8
After 1 Week	1.8	15.9
After 2 Weeks	2.6	27.2
After 4 Weeks	3.7	31.7
After 8 Weeks	5.9	54.5

From the values of ΔE shown in Table IV, it was found that the color change was inhibited by blending sodium hypophosphite.

As explained above, the aromatic polyamide resin composition of the present invention can provide a molded article with an excellent balance in toughness and stiffness without the formation of warping in the molded article while the high heat resistance, which the aromatic polyamide particularly has, can be maintained.

Claims

1. An aromatic polyamide resin composition comprising an aromatic polyamide resin having a melting point of at least 290°C, an inorganic filler, and an impact modifier wherein the composition has a ratio of the weight M of said inorganic filler to the weight T of said impact of $2.0 \leq M/T \leq 6.5$.
- 5 2. An aromatic polyamide resin composition of claim 1 wherein the composition has a melt viscosity, measured with a capillary rheometer at a shear rate of 1000/sec and a process temperature 20-30°C higher than the melting point of said aromatic polyamide resin, of 350 Pa·sec or less.
- 10 3. An aromatic polyamide resin composition of claim 1-2 wherein said aromatic polyamide resin has a glass transition temperature of at least 60°C.

DECLARATION and POWER OF ATTORNEY

As a below-named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

AROMATIC POLYAMIDE RESIN COMPOSITION HAVING EXCELLENT BALANCE OF TOUGHNESS AND STIFFNESS

the specification of which is attached hereto unless the following box is checked:

☐ was filed on _____ as U.S. Application No. _____ or PCT International Application No. _____ and was amended on _____ (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is known to me to be material to patentability as defined in 37 CFR § 1.56.

I hereby claim foreign priority benefits under 35 U.S.C. § 119(a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate, or § 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed.

Application No.	Country	Filing Date	Priority Claimed (Yes/No)
8-130342	JAPAN	24 MAY 1996	Yes

I hereby claim the benefit under 35 U.S.C. § 119(e) of any United States Provisional Application(s) listed below.

U.S. Provisional Application No.	U.S. Filing Date

I hereby claim the benefit under 35 U.S.C. § 120 of any United States application(s), or § 365(c) of any PCT International Application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application or PCT International Application in the manner provided by the first paragraph of 35 U.S.C. § 112, I acknowledge the duty to disclose information which is known to me to be material to patentability as defined in 37 CFR § 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application.

Application No.	Filing Date	Status (patented, pending or abandoned)
PCT/US97/09090	16 MAY 1997	Pending

POWER OF ATTORNEY: I hereby appoint the following attorney(s) and/or agent(s) the power to prosecute this application and transact all business in the Patent and Trademark Office connected therewith:

Name: JAMES A. FORSTNER	Registration No.: 24,259
-------------------------	--------------------------

Send correspondence and direct telephone calls to:

JAMES A. FORSTNER

E. I. du Pont de Nemours and Company
Legal - Patents
 Wilmington, DE 19898, U.S.A.

Tel. No.
 (302) 773-0686

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

INVENTOR(S)

Full Name of Inventor	Last Name NOZAKI	First Name MASAHIRO	Middle Name
Signature (please sign full name): <i>Masahiro Nozaki</i>			Date: 15 July 1997
Residence & Citizenship	City TOCHIGI-KEN	State or Foreign Country JAPAN	Country of Citizenship JAPAN
Post Office Address	Post Office Address EAST SUZUMI B-305 342-1 HIRAMATSU-HONCHO, UTSUNOMIYA-SHI	City TOCHIGI-KEN	State or Country JAPAN
			Zip Code 321

☐ Additional Inventors are being named on separately numbered sheets attached hereto.